

RC Assay Results - Gold, Silver & Key Pathfinders
GT Gold Saddle Project
Tatogga Property, Iskut, BC
2017

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR001	0.00	1.07	1.07	V750001	4.9	5.27	17.3	229	3	207	1110	78	506
TTR001	1.07	2.59	1.52	V750002	2.4		5.8	84	1	112	235	18	364
TTR001	2.59	4.11	1.52	V750003	1.37		2.1	84	3	146	130	7	555
TTR001	4.11	5.64	1.52	V750004	0.71		2	72	1	147	100	11	742
TTR001	5.64	7.16	1.52	V750005	0.12		0.25	12	1	71	19	2.5	515
TTR001	7.16	8.69	1.52	V750006	0.19		0.25	12	1	73	30	2.5	230
TTR001	8.69	10.06	1.37	V750007	0.15		0.25	11	2	48	17	2.5	166
TTR002	0.00	1.22	1.22	V750008		2.02							
TTR002	1.22	2.74	1.52	V750009		0.26							
TTR002	2.74	4.27	1.52	V750010		0.25							
TTR002	4.27	5.79	1.52	V750011		0.47							
TTR002	5.79	7.32	1.52	V750012		0.19							
TTR002	7.32	8.84	1.52	V750013		0.05							
TTR002	8.84	10.36	1.52	V750014		0.05							
TTR002	10.36	11.89	1.52	V750016		0.025							
TTR002	11.89	13.41	1.52	V750017		0.025							
TTR002	13.41	14.94	1.52	V750018		0.025							
TTR002	14.94	15.70	0.76	V750019		0.025							
TTR002	15.70	16.76	1.06	V750022		0.025							
TTR003	0.00	0.91	0.91	V750023		0.32							
TTR003	0.91	2.44	1.52	V750024		0.39							
TTR003	2.44	3.96	1.52	V750025		0.025							
TTR003	3.96	5.49	1.52	V750026		0.025							
TTR003	5.49	7.01	1.52	V750027		0.025							
TTR003	7.01	8.53	1.52	V750028		0.025							
TTR003	8.53	9.30	0.76	V750029		0.025							
TTR003	9.30	10.82	1.52	V750031		0.025							
TTR003	10.82	12.34	1.52	V750032		0.025							
TTR003	12.34	13.87	1.53	V750033		0.025							
TTR004	0.00	0.91	0.91	V750036		0.06							
TTR004	0.91	2.44	1.52	V750037		0.025							
TTR004	2.44	3.96	1.52	V750038		0.025							
TTR004	3.96	4.72	0.76	V750039		0.025							
TTR004	4.72	6.25	1.52	V750040		0.025							
TTR004	6.25	7.77	1.52	V750041		0.025							
TTR004	7.77	9.30	1.52	V750042		0.025							
TTR004	9.30	10.82	1.52	V750043		0.025							
TTR004	10.82	12.34	1.52	V750044		0.025							
TTR004	12.34	13.87	1.53	V750046		0.025							
TTR005	0.00	2.44	2.44	V750047		0.025							
TTR005	2.44	3.96	1.52	V750048		0.025							
TTR005	3.96	5.49	1.52	V750049		0.025							
TTR005	5.49	7.01	1.52	V750050		0.025							
TTR005	7.01	7.77	0.76	V750051		0.025							
TTR005	7.77	9.30	1.52	V750052		0.025							
TTR005	9.30	10.82	1.52	V750053		0.06							
TTR005	10.82	12.34	1.52	V750054		0.025							
TTR005	12.34	13.87	1.52	V750055		0.025							
TTR005	13.87	15.85	1.98	V750056		0.025							
TTR005	15.85	17.37	1.52	V750057		0.025							
TTR005	17.37	18.90	1.52	V750058		0.025							
TTR005	18.90	20.42	1.52	V750059		0.025							
TTR005	20.42	21.95	1.52	V750061		0.025							
TTR005	21.95	23.47	1.52	V750062		0.025							
TTR005	23.47	24.99	1.52	V750063		0.025							
TTR005	24.99	26.52	1.53	V750064		0.025							

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR006	0.00	1.22	1.22	V750067		0.025							
TTR006	1.22	2.74	1.52	V750068		0.06							
TTR006	2.74	4.27	1.52	V750069		0.025							
TTR006	4.27	5.79	1.52	V750070		0.025							
TTR006	5.79	7.32	1.52	V750071		0.025							
TTR006	7.32	8.84	1.52	V750072		0.025							
TTR006	8.84	10.36	1.52	V750073		0.025							
TTR006	10.36	11.89	1.52	V750074		0.025							
TTR006	11.89	13.41	1.52	V750076		0.025							
TTR006	13.41	15.24	1.83	V750077		0.025							
TTR006	15.24	15.85	0.61	V750078		0.025							
TTR006	15.85	17.37	1.52	V750079		0.025							
TTR006	17.37	18.90	1.53	V750080		0.025							
TTR007	0.00	0.91	0.91	V750081	0.11		0.25	22	1	56	15	2.5	201
TTR007	0.91	2.44	1.52	V750082	0.13		0.25	32	1	65	18	2.5	218
TTR007	2.44	3.96	1.52	V750083	0.23		0.25	27	1	69	32	2.5	331
TTR007	3.96	5.49	1.52	V750084	0.48		0.7	53	1	72	102	2.5	320
TTR007	5.49	5.79	0.3	V750085	0.03		0.25	16	1	22	7	2.5	116
TTR008	0.00	0.91	0.91	V750086	0.12		0.25	40	2	101	18	2.5	199
TTR008	0.91	2.44	1.52	V750087	0.64		2.2	45	1	74	71	14	262
TTR008	2.44	3.96	1.52	V750088	2.46		4	117	1	83	343	14	487
TTR008	3.96	4.88	0.91	V750089	0.77		0.8	49	1	114	41	5	596
TTR008	4.88	5.49	0.61	V750091	1.16		1.2	130	1	81	83	7	211
TTR008	5.49	7.01	1.52	V750092	6.94	2.03	4.4	536	3	210	807	15	1785
TTR008	7.01	8.23	1.22	V750093	3.91	3.76	2.9	521	1	185	418	11	1670
TTR008	8.23	9.75	1.52	V750094	3.36	4.01	3.5	703	1	191	3070	11	4350
TTR008	9.75	11.28	1.52	V750095	8.87	9.33	7.3	1170	1	742	3110	16	2330
TTR008	11.28	12.80	1.52	V750096	17.9	18.65	28.1	1450	6	932	1740	101	6190
TTR008	12.80	14.33	1.52	V750097	41.6	41.3	144	1405	35	6970	7890	1230	23300
TTR008	14.33	15.85	1.52	V750098	8.62	8.51	8	630	1	650	491	28	651
TTR008	15.85	17.37	1.52	V750099	0.57		1	94	1	63	65	11	128
TTR008	17.37	18.90	1.52	V750100	0.46		1	72	1	25	32	7	77
TTR008	18.90	20.42	1.52	V750101	0.23		0.25	56	1	65	20	10	60
TTR008	20.42	21.95	1.52	V750102	0.08		0.25	15	1	25	15	2.5	84
TTR008	21.95	23.47	1.52	V750103	0.04		0.25	13	1	23	12	7	97
TTR008	23.47	24.99	1.52	V750104	0.06		0.25	12	1	30	7	2.5	96
TTR008	24.99	26.52	1.52	V750106	0.07		0.25	16	1	29	7	2.5	93
TTR008	26.52	28.04	1.52	V750107	0.08		0.25	15	1	22	6	2.5	76
TTR008	28.04	29.57	1.52	V750108	1.13		1	177	1	70	72	5	102
TTR008	29.57	31.09	1.52	V750109	1.34		0.8	159	1	82	85	6	120
TTR008	31.09	32.61	1.52	V750110	0.53		0.25	194	5	39	30	2.5	68
TTR008	32.61	34.14	1.52	V750111	0.04		0.25	16	1	10	10	2.5	54
TTR008	34.14	35.66	1.52	V750112	0.02		0.25	9	1	27	22	2.5	75
TTR008	35.66	37.19	1.52	V750113	0.03		0.25	11	4	13	9	2.5	46
TTR008	37.19	38.71	1.52	V750114	0.02		0.25	14	6	14	8	2.5	40
TTR008	38.71	40.23	1.52	V750115	0.01		0.25	8	3	7	5	2.5	34
TTR008	40.23	41.76	1.52	V750116	0.06		0.25	161	4	9	8	2.5	25
TTR008	41.76	43.28	1.52	V750117	2.05	2.47	2.1	565	3	206	87	2.5	85
TTR008	43.28	44.81	1.52	V750118	3.95	3.87	3.4	521	8	3790	76	6	50
TTR008	44.81	46.33	1.52	V750119	0.49		0.7	56	4	2950	12	2.5	19
TTR008	46.33	47.85	1.52	V750121	0.11		0.25	22	1	27	6	2.5	71
TTR008	47.85	49.38	1.52	V750122	0.1		0.25	25	1	13	5	2.5	71
TTR008	49.38	50.90	1.52	V750123	0.27		0.25	44	3	9	7	2.5	78
TTR008	50.90	52.43	1.52	V750124	0.11		0.25	9	4	4	4	2.5	62
TTR008	52.43	53.95	1.52	V750125	0.08		0.25	42	3	17	8	2.5	75
TTR008	53.95	55.47	1.52	V750126	0.43		0.25	17	1	11	4	2.5	63
TTR008	55.47	57.00	1.52	V750127	0.03		0.25	9	1	3	1	2.5	49
TTR008	57.00	58.52	1.52	V750128	0.01		0.25	2.5	2	3	3	2.5	57
TTR008	58.52	60.05	1.53	V750129	0.1		0.25	15	1	11	5	2.5	60
TTR009	0.00	2.44	2.44	V750132		0.1							
TTR009	2.44	3.96	1.52	V750133		0.15							

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR009	3.96	5.49	1.52	V750134		0.38							
TTR009	5.49	7.01	1.52	V750136		0.32							
TTR009	7.01	8.53	1.52	V750137		0.12							
TTR009	8.53	10.06	1.52	V750138		0.025							
TTR009	10.06	11.58	1.52	V750139		0.025							
TTR009	11.58	13.11	1.52	V750140		0.025							
TTR009	13.11	14.63	1.52	V750141		0.025							
TTR009	14.63	16.15	1.52	V750142		0.025							
TTR009	16.15	17.37	1.22	V750143		0.025							
TTR009	17.37	18.90	1.52	V750144		0.025							
TTR009	18.90	20.42	1.52	V750145		0.025							
TTR009	20.42	21.95	1.52	V750146		0.025							
TTR009	21.95	23.47	1.52	V750147		0.025							
TTR009	23.47	24.99	1.52	V750148		0.025							
TTR009	24.99	26.52	1.52	V750149		0.06							
TTR009	26.52	28.04	1.52	V750151		0.06							
TTR009	28.04	29.57	1.52	V750152		0.06							
TTR009	29.57	31.09	1.52	V750153		0.15							
TTR009	31.09	32.61	1.52	V750154		0.09							
TTR009	32.61	34.14	1.52	V750155		0.14							
TTR009	34.14	35.66	1.52	V750156		0.07							
TTR009	35.66	37.19	1.52	V750157		0.05							
TTR009	37.19	38.71	1.52	V750158		0.025							
TTR009	38.71	40.23	1.52	V750159		0.025							
TTR009	40.23	41.76	1.52	V750160		0.97							
TTR009	41.76	43.28	1.52	V750161		0.05							
TTR009	43.28	44.81	1.52	V750162		0.025							
TTR009	44.81	46.33	1.52	V750163		0.025							
TTR009	46.33	47.85	1.52	V750164		0.08							
TTR010	0.00	0.91	0.91	V750166	0.07		0.25	15	4	66	12	2.5	131
TTR010	0.91	2.44	1.52	V750167	0.13		0.25	28	1	79	11	2.5	162
TTR010	2.44	3.96	1.52	V750168	0.23		0.25	35	5	94	19	2.5	186
TTR010	3.96	5.49	1.52	V750169	0.31		0.25	67	3	86	24	2.5	165
TTR010	5.49	7.01	1.52	V750170	0.03		0.25	2.5	2	50	3	2.5	172
TTR010	7.01	8.53	1.52	V750171	0.01		0.25	2.5	4	40	3	2.5	151
TTR010	8.53	9.75	1.22	V750172	0.02		0.25	5	4	23	3	2.5	136
TTR010	9.75	11.28	1.52	V750173	0.01		0.25	5	3	63	5	2.5	110
TTR010	11.28	12.80	1.52	V750174	0.03		0.25	8	5	37	6	2.5	112
TTR010	12.80	14.33	1.52	V750175	0.09		0.25	5	4	21	1	2.5	96
TTR010	14.33	16.00	1.68	V750176	0.13		0.25	15	2	66	4	2.5	86
TTR010	16.00	17.53	1.52	V750177	0.08		0.25	7	2	29	3	2.5	88
TTR010	17.53	19.05	1.52	V750178	0.05		0.25	7	1	12	5	2.5	73
TTR010	19.05	20.57	1.52	V750179	0.03		0.25	5	3	3	4	2.5	72
TTR010	20.57	22.10	1.52	V750181	0.02		0.25	2.5	1	55	1	2.5	65
TTR010	22.10	23.62	1.52	V750182	0.01		0.25	2.5	1	5	1	5	61
TTR010	23.62	25.15	1.52	V750183	0.01		0.25	6	1	8	3	2.5	64
TTR010	25.15	26.67	1.52	V750184	0.005		0.25	6	1	21	11	2.5	118
TTR010	26.67	28.19	1.52	V750185	0.02		0.25	2.5	1	9	3	2.5	91
TTR010	28.19	29.72	1.52	V750186	0.01		0.25	2.5	1	6	4	2.5	83
TTR010	29.72	31.24	1.52	V750187	0.01		0.25	2.5	1	2	5	2.5	88
TTR010	31.24	32.77	1.52	V750188	0.005		0.25	2.5	1	4	7	2.5	87
TTR010	32.77	34.29	1.52	V750189	0.005		0.25	2.5	1	4	1	5	57
TTR010	34.29	35.81	1.52	V750190	0.05		0.25	20	1	4	3	2.5	70
TTR010	35.81	37.34	1.52	V750191	0.005		0.25	2.5	1	1	2	2.5	60
TTR010	37.34	38.86	1.52	V750192	0.05		0.25	10	1	4	1	2.5	62
TTR010	38.86	40.39	1.52	V750193	0.05		0.25	8	1	4	4	2.5	65
TTR010	40.39	41.91	1.52	V750194	0.05		0.25	11	1	12	1	2.5	80
TTR010	41.91	43.43	1.52	V750196	0.27		0.25	20	1	10	7	6	77
TTR010	43.43	44.96	1.52	V750197	0.14		0.25	38	1	34	5	2.5	87
TTR010	44.96	46.48	1.52	V750198	0.04		0.25	10	1	5	1	2.5	85
TTR010	46.48	48.01	1.52	V750199	0.14		0.25	9	1	10	2	5	87

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR010	48.01	49.53	1.52	V750200	0.31		0.25	12	1	5	4	2.5	74
TTR010	49.53	51.05	1.52	V750201	0.37		0.25	27	1	12	8	2.5	104
TTR010	51.05	52.58	1.52	V750202	0.05		0.25	6	1	4	3	2.5	83
TTR010	52.58	54.10	1.52	V750203	0.18		0.25	12	1	30	1	2.5	72
TTR010	54.10	55.63	1.52	V750204	0.05		0.25	6	1	16	3	2.5	72
TTR010	55.63	57.15	1.52	V750205	1.22		0.7	77	1	33	10	2.5	53
TTR010	57.15	58.67	1.52	V750206	0.16		0.25	18	1	22	6	2.5	52
TTR010	58.67	60.20	1.52	V750207	0.15		0.25	19	1	38	7	6	78
TTR010	60.20	61.72	1.52	V750208	0.06		0.25	7	1	11	3	9	103
TTR010	61.72	63.25	1.52	V750209	0.03		0.8	11	1	693	4	2.5	107
TTR010	63.25	64.77	1.52	V750211	0.04		0.25	5	1	119	1	2.5	99
TTR010	64.77	66.29	1.52	V750212	0.15		0.6	107	1	209	39	2.5	117
TTR010	66.29	67.82	1.52	V750213	0.22		0.25	59	1	149	19	2.5	244
TTR010	67.82	69.34	1.52	V750214	0.59		0.7	74	1	164	20	2.5	178
TTR010	69.34	70.87	1.52	V750215	0.13		0.25	25	1	60	5	7	130
TTR010	70.87	72.39	1.52	V750216	1.81	1.87	3.2	407	4	127	919	13	1670
TTR010	72.39	73.91	1.52	V750217	3.05	2.56	5.3	580	7	122	2070	10	2340
TTR010	73.91	75.44	1.52	V750218	2.64	2.7	6.2	596	5	249	1860	15	3650
TTR010	75.44	76.96	1.52	V750219	2.34	2.36	5.7	696	1	244	2320	16	3520
TTR010	76.96	78.49	1.53	V750220	0.33		0.5	116	1	36	314	8	629
TTR011	0.00	2.44	2.44	V750223	0.09		0.25	21	1	74	19	2.5	189
TTR011	2.44	3.96	1.52	V750224	0.03		0.25	13	1	61	11	2.5	107
TTR011	3.96	5.49	1.52	V750226	0.04		0.25	12	1	53	10	2.5	112
TTR011	5.49	7.01	1.52	V750227	0.16		0.25	12	1	54	10	2.5	140
TTR011	7.01	8.53	1.52	V750228	0.25		0.25	13	1	55	8	2.5	104
TTR011	8.53	10.06	1.52	V750229	0.02		0.25	11	3	57	12	2.5	121
TTR011	10.06	11.58	1.52	V750230	0.04		0.25	17	3	69	21	2.5	131
TTR011	11.58	13.11	1.52	V750231	0.03		0.25	9	1	59	13	2.5	108
TTR011	13.11	14.33	1.22	V750232	0.02		0.25	5	1	44	4	2.5	86
TTR011	14.33	15.85	1.52	V750233	0.02		0.25	10	2	67	15	2.5	93
TTR011	15.85	17.37	1.52	V750234	0.02		0.25	8	1	57	9	2.5	98
TTR011	17.37	18.90	1.52	V750235	0.03		0.25	10	2	67	6	2.5	97
TTR011	18.90	20.42	1.52	V750236	0.03		0.25	8	3	23	4	2.5	83
TTR011	20.42	21.95	1.52	V750237	0.02		0.25	2.5	3	17	2	2.5	57
TTR011	21.95	23.47	1.52	V750238	0.04		0.25	8	1	9	3	2.5	60
TTR011	23.47	24.99	1.52	V750239	0.02		0.25	6	1	7	2	2.5	52
TTR011	24.99	26.52	1.52	V750241	0.005		0.25	7	5	4	3	2.5	60
TTR011	26.52	28.04	1.52	V750242	0.01		0.25	6	1	2	4	2.5	63
TTR011	28.04	29.57	1.52	V750243	0.01		0.25	6	3	1	2	2.5	66
TTR011	29.57	31.09	1.52	V750244	0.04		0.25	6	1	4	8	2.5	67
TTR011	31.09	32.61	1.52	V750245	0.01		0.25	2.5	2	34	4	6	64
TTR011	32.61	34.14	1.52	V750246	0.01		0.25	5	1	7	2	2.5	70
TTR011	34.14	35.66	1.52	V750247	0.005		0.25	11	1	3	3	2.5	70
TTR011	35.66	37.19	1.52	V750248	0.37		0.7	151	2	90	23	6	84
TTR011	37.19	38.71	1.52	V750249	1.12		1.2	298	2	43	62	10	344
TTR011	38.71	40.23	1.52	V750250	0.66		1.4	355	1	51	61	7	144
TTR011	40.23	41.76	1.52	V750251	3.96	3.78	3.8	865	2	214	424	12	333
TTR011	41.76	43.28	1.52	V750252	1.86	1.92	2.1	518	4	84	145	10	138
TTR011	43.28	44.81	1.52	V750253	2.19	2.21	2.3	580	2	122	137	17	80
TTR011	44.81	46.33	1.52	V750254	0.15		0.25	68	1	16	20	21	42
TTR011	46.33	47.85	1.52	V750256	0.03		0.25	37	1	6	9	14	34
TTR011	47.85	49.38	1.52	V750257	0.01		0.25	26	1	11	8	14	25
TTR011	49.38	50.90	1.52	V750258	0.01		0.25	36	1	5	7	12	24
TTR011	50.90	52.43	1.52	V750259	0.02		0.25	25	1	9	7	13	24
TTR011	52.43	53.95	1.52	V750260	0.02		0.25	31	1	16	9	23	20
TTR011	53.95	55.47	1.52	V750261	0.01		0.25	21	2	49	11	24	32
TTR011	55.47	57.00	1.52	V750262	0.01		0.25	31	1	49	5	12	21
TTR011	57.00	58.52	1.52	V750263	0.005		0.25	27	1	55	2	18	24
TTR011	58.52	60.05	1.52	V750264	0.01		0.25	24	1	9	7	7	43
TTR011	60.05	61.57	1.52	V750265	0.16		0.25	34	1	15	9	5	39
TTR011	61.57	63.09	1.52	V750266	0.05		0.25	23	1	25	8	7	62

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR011	63.09	64.62	1.52	V750267	0.01		0.25	12	1	8	5	2.5	36
TTR011	64.62	66.14	1.52	V750268	0.005		0.25	2.5	1	4	1	6	22
TTR011	66.14	67.67	1.52	V750269	0.005		0.25	8	1	19	5	2.5	35
TTR011	67.67	69.19	1.52	V750271	0.01		0.25	10	1	43	12	2.5	79
TTR011	69.19	70.71	1.52	V750272	0.33		0.25	176	1	18	9	2.5	46
TTR011	70.71	72.24	1.52	V750273	0.17		0.25	23	5	11	2	2.5	45
TTR011	72.24	73.76	1.52	V750274	0.47		0.25	25	2	22	1	2.5	35
TTR011	73.76	75.29	1.52	V750275	0.67		0.25	52	1	20	3	2.5	29
TTR011	75.29	76.81	1.52	V750276	0.13		0.25	32	1	11	2	2.5	26
TTR011	76.81	78.33	1.52	V750277	0.22		0.25	150	2	10	1	2.5	21
TTR011	78.33	79.86	1.52	V750278	0.26		0.25	28	1	6	1	2.5	20
TTR011	79.86	81.38	1.52	V750279	0.22		0.25	14	1	7	1	2.5	27
TTR011	81.38	82.91	1.53	V750280	0.39		0.25	9	1	7	1	2.5	25
TTR012	0.00	2.44	2.44	V750281		0.025							
TTR012	2.44	3.96	1.52	V750282		0.025							
TTR012	3.96	5.49	1.52	V750283		0.025							
TTR012	5.49	7.01	1.52	V750284		0.025							
TTR012	7.01	8.53	1.52	V750286		0.025							
TTR012	8.53	10.06	1.52	V750287		0.025							
TTR012	10.06	11.58	1.52	V750288		0.025							
TTR012	11.58	13.11	1.52	V750289		0.025							
TTR012	13.11	14.63	1.52	V750290		0.025							
TTR012	14.63	15.85	1.22	V750291		0.025							
TTR012	15.85	17.37	1.52	V750292		0.025							
TTR012	17.37	18.90	1.52	V750293		0.025							
TTR012	18.90	20.42	1.52	V750294		0.025							
TTR012	20.42	21.95	1.52	V750295		0.025							
TTR012	21.95	23.47	1.52	V750296		0.025							
TTR012	23.47	24.99	1.52	V750297		0.09							
TTR012	24.99	26.52	1.52	V750298		0.06							
TTR012	26.52	28.04	1.52	V750299		0.025							
TTR012	28.04	29.57	1.52	V750301		0.025							
TTR012	29.57	31.09	1.52	V750302		0.025							
TTR012	31.09	32.61	1.52	V750303		0.025							
TTR012	32.61	34.14	1.52	V750304		0.025							
TTR012	34.14	35.66	1.52	V750305		0.025							
TTR012	35.66	37.19	1.52	V750306		0.025							
TTR012	37.19	38.71	1.52	V750307		0.025							
TTR012	38.71	40.23	1.52	V750308		0.025							
TTR012	40.23	41.76	1.52	V750309		0.025							
TTR012	41.76	43.28	1.52	V750310		0.025							
TTR012	43.28	44.81	1.52	V750311		0.025							
TTR012	44.81	46.33	1.52	V750312		0.12							
TTR012	46.33	47.85	1.52	V750313		0.025							
TTR012	47.85	49.38	1.52	V750314		0.07							
TTR012	49.38	50.90	1.52	V750316		0.08							
TTR012	50.90	52.43	1.52	V750317		0.025							
TTR012	52.43	53.95	1.52	V750318		0.025							
TTR012	53.95	55.47	1.52	V750319		0.025							
TTR012	55.47	57.00	1.52	V750320		0.9							
TTR012	57.00	58.52	1.52	V750321		0.19							
TTR012	58.52	60.05	1.52	V750322		0.12							
TTR012	60.05	61.57	1.52	V750323		0.18							
TTR013	0.00	2.44	2.44	V750326	0.04		0.25	12	1	56	1	2.5	101
TTR013	2.44	5.49	3.05	V750327	0.02		0.25	8	1	71	1	2.5	83
TTR013	5.49	7.01	1.52	V750328	0.05		0.25	6	2	60	3	2.5	77
TTR013	7.01	8.53	1.52	V750329	0.01		0.25	10	1	96	3	2.5	77
TTR013	8.53	10.06	1.52	V750331	0.03		0.25	8	2	71	3	2.5	84
TTR013	10.06	11.58	1.52	V750332	0.005		0.25	10	1	105	3	2.5	77
TTR013	11.58	13.11	1.52	V750333	0.01		0.25	7	1	90	5	2.5	92
TTR013	13.11	14.63	1.52	V750334	0.04		0.25	7	1	27	4	2.5	93

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR013	14.63	16.15	1.52	V750335	0.13		0.25	17	1	26	6	2.5	149
TTR013	16.15	17.68	1.52	V750336	0.05		0.25	2.5	1	31	1	2.5	149
TTR013	17.68	19.20	1.52	V750337	5.23	4.68	97.7	909	7	2730	323	679	2160
TTR013	19.20	20.12	0.91	V750338	16	20.7	14.7	1135	5	2340	925	42	810
TTR013	20.12	21.64	1.52	V750339	19.3	18.85	19	929	1	1240	3080	46	3450
TTR013	21.64	23.16	1.52	V750340	7.48		8.8	635	6	1470	1275	22	1165
TTR013	23.16	24.69	1.52	V750341	3.03	4.18	7.5	616	2	2150	1505	16	2680
TTR013	24.69	26.21	1.52	V750342	4.34	4.5	9.8	537	1	1790	3190	23	6640
TTR013	26.21	27.74	1.52	V750343	0.43		0.25	66	3	61	79	2.5	223
TTR013	27.74	29.26	1.52	V750344	0.07		0.25	24	2	31	18	2.5	108
TTR013	29.26	30.78	1.52	V750346	0.39		0.25	20	1	28	22	2.5	104
TTR013	30.78	32.31	1.52	V750347	0.06		0.25	7	1	4	3	2.5	65
TTR013	32.31	33.83	1.52	V750348	0.66		0.25	47	1	60	52	2.5	110
TTR013	33.83	35.36	1.52	V750349	1.09		0.25	106	1	21	11	2.5	84
TTR013	35.36	36.88	1.52	V750350	0.06		0.25	16	3	3	4	2.5	82
TTR013	36.88	38.40	1.52	V750351	0.36		0.25	46	3	9	8	2.5	65
TTR013	38.40	39.93	1.52	V750352	0.25		0.25	62	1	8	7	2.5	64
TTR013	39.93	41.45	1.52	V750353	0.1		0.25	43	1	4	1	2.5	63
TTR013	41.45	42.98	1.52	V750354	0.04		0.25	20	3	9	1	2.5	50
TTR013	42.98	44.50	1.52	V750355	0.08		0.25	35	1	6	2	2.5	69
TTR013	44.50	46.02	1.52	V750356	0.03		0.25	21	1	24	3	2.5	46
TTR013	46.02	47.55	1.52	V750357	0.01		0.25	6	4	16	4	2.5	90
TTR013	47.55	49.07	1.52	V750358	0.07		0.25	15	3	5	1	2.5	69
TTR013	49.07	50.60	1.52	V750359	0.52		0.25	37	2	69	71	2.5	112
TTR013	50.60	52.12	1.52	V750361	0.05		0.25	5	3	17	2	2.5	75
TTR013	52.12	53.64	1.52	V750362	0.05		0.25	8	1	18	1	2.5	75
TTR013	53.64	55.17	1.52	V750363	0.03		0.25	5	1	18	1	2.5	75
TTR013	55.17	56.69	1.52	V750364	0.01		0.25	2.5	1	16	1	2.5	57
TTR013	56.69	58.22	1.52	V750365	0.27		0.25	28	1	41	32	2.5	73
TTR013	58.22	60.05	1.83	V750366	0.15		0.25	19	1	195	14	2.5	74
TTR013	60.05	61.26	1.22	V750367	0.06		0.25	9	1	58	3	2.5	56
TTR013	61.26	62.79	1.52	V750368	0.04		0.25	9	1	23	4	2.5	48
TTR013	62.79	64.31	1.52	V750369	0.04		0.25	8	1	25	5	2.5	51
TTR013	64.31	65.84	1.52	V750370	0.07		0.25	9	1	133	8	2.5	69
TTR013	65.84	67.36	1.52	V750371	0.04		0.25	2.5	1	14	3	2.5	56
TTR013	67.36	68.88	1.52	V750372	0.03		0.25	5	1	9	3	2.5	54
TTR013	68.88	70.41	1.52	V750373	0.01		0.25	5	1	17	1	2.5	45
TTR013	70.41	71.93	1.52	V750374	0.01		0.25	2.5	1	10	1	2.5	33
TTR014	0.00	2.44	2.44	V750378	0.03		0.25	6	1	47	8	2.5	91
TTR014	2.44	3.96	1.52	V750379	0.03		0.25	6	1	57	5	2.5	93
TTR014	3.96	5.49	1.52	V750380	0.03		0.25	8	1	53	5	2.5	78
TTR014	5.49	7.01	1.52	V750381	0.01		0.25	13	1	90	4	2.5	90
TTR014	7.01	8.53	1.52	V750382	0.02		0.25	11	3	106	7	6	97
TTR014	8.53	10.06	1.52	V750383	0.02		0.25	2.5	1	66	5	2.5	91
TTR014	10.06	11.28	1.22	V750384	0.04		0.25	6	1	33	8	2.5	102
TTR014	11.28	12.80	1.52	V750385	0.01		0.25	2.5	1	32	1	2.5	89
TTR014	12.80	14.33	1.52	V750386	0.05		0.25	11	1	76	18	2.5	193
TTR014	14.33	15.85	1.52	V750387	0.05		0.25	7	1	68	7	2.5	330
TTR014	15.85	17.37	1.52	V750388	0.04		0.25	8	1	341	8	2.5	310
TTR014	17.37	18.90	1.52	V750389	0.02		0.25	2.5	1	489	2	2.5	127
TTR014	18.90	20.42	1.52	V750391	0.02		0.25	2.5	1	35	1	2.5	113
TTR014	20.42	21.95	1.52	V750392	0.01		0.25	2.5	1	52	1	2.5	131
TTR014	21.95	23.47	1.52	V750393	0.01		0.25	5	1	24	2	2.5	162
TTR014	23.47	24.99	1.52	V750394	0.12		0.25	41	3	20	8	2.5	159
TTR014	24.99	26.52	1.52	V750395	0.03		0.25	20	1	4	6	2.5	109
TTR014	26.52	28.04	1.52	V750396	0.08		0.25	7	1	14	3	2.5	108
TTR014	28.04	29.57	1.52	V750397	0.04		0.25	5	1	2	1	2.5	103
TTR014	29.57	31.09	1.52	V750398	0.05		0.25	2.5	1	12	4	2.5	92
TTR014	31.09	32.61	1.52	V750399	0.08		0.25	26	1	10	6	2.5	80
TTR014	32.61	34.14	1.52	V750400	0.06		0.25	15	1	12	7	2.5	88
TTR014	34.14	35.66	1.52	V750401	0.06		0.25	20	2	15	7	2.5	106

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR014	35.66	37.19	1.52	V750402	0.03		0.25	11	3	10	5	2.5	49
TTR014	37.19	38.71	1.52	V750403	0.05		0.25	11	2	12	6	2.5	60
TTR014	38.71	40.23	1.52	V750404	0.12		0.25	7	1	60	2	2.5	50
TTR014	40.23	41.76	1.52	V750406	0.07		0.25	5	5	602	4	2.5	57
TTR014	41.76	43.28	1.52	V750407	0.13		0.25	39	2	607	8	2.5	65
TTR014	43.28	44.81	1.52	V750408	0.07		0.25	11	1	176	4	2.5	67
TTR014	44.81	46.33	1.52	V750409	0.05		0.25	2.5	4	48	2	2.5	66
TTR014	46.33	47.85	1.52	V750410	0.09		0.25	35	1	27	8	2.5	51
TTR014	47.85	49.38	1.52	V750411	0.07		0.25	24	2	15	8	2.5	68
TTR014	49.38	50.90	1.52	V750412	0.16		0.25	27	2	26	7	2.5	67
TTR014	50.90	52.43	1.52	V750413	3.5		1.7	225	1	80	47	2.5	103
TTR014	52.43	53.95	1.52	V750414	0.03		0.25	8	1	24	7	2.5	61
TTR014	53.95	55.47	1.52	V750415	0.03		0.25	11	4	27	1	2.5	54
TTR014	55.47	57.00	1.52	V750416	0.49		0.25	45	4	45	7	2.5	45
TTR014	57.00	58.52	1.52	V750417	0.01		0.25	16	4	23	18	2.5	136
TTR014	58.52	60.05	1.52	V750418	0.17		0.25	59	1	55	42	2.5	139
TTR014	60.05	61.57	1.52	V750419	0.79		0.25	155	1	39	66	2.5	127
TTR014	61.57	63.09	1.52	V750421	0.34		0.25	132	1	32	21	2.5	114
TTR014	63.09	64.62	1.52	V750422	0.01		0.25	22	1	13	11	2.5	117
TTR014	64.62	66.14	1.52	V750423	1.46		0.9	296	1	97	53	2.5	105
TTR014	66.14	67.67	1.52	V750424	0.02		0.25	19	3	54	8	2.5	60
TTR014	67.67	69.19	1.52	V750425	3.85		1.2	243	3	600	31	2.5	121
TTR014	69.19	70.71	1.52	V750426	0.08		0.25	28	1	91	6	2.5	73
TTR014	70.71	72.24	1.52	V750427	0.07		0.25	66	4	10	8	2.5	103
TTR014	72.24	73.76	1.52	V750428	1.49	1.45	1.2	402	1	181	114	2.5	120
TTR014	73.76	75.29	1.52	V750429	0.08		0.25	51	4	16	13	2.5	116
TTR014	75.29	76.81	1.52	V750430	0.03		0.25	14	1	5	6	2.5	88
TTR014	76.81	78.33	1.52	V750431	0.08		0.25	49	2	9	30	2.5	198
TTR014	78.33	79.86	1.52	V750432	0.02		0.25	6	1	14	16	2.5	177
TTR014	79.86	81.38	1.52	V750433	0.01		0.25	11	1	8	9	2.5	183
TTR015	0.00	0.91	0.91	V750437	0.05		0.25	16	4	44	6	5	98
TTR015	0.91	2.44	1.52	V750438	0.01		0.25	7	2	22	11	2.5	61
TTR015	2.44	3.96	1.52	V750439	0.01		0.25	5	4	58	8	2.5	84
TTR015	3.96	5.49	1.52	V750440	0.01		0.25	7	3	72	1	2.5	78
TTR015	5.49	7.01	1.52	V750441	0.005		0.25	8	6	105	1	2.5	78
TTR015	7.01	8.53	1.52	V750442	0.005		0.25	9	4	63	1	2.5	76
TTR015	8.53	10.06	1.52	V750443	0.03		0.25	7	2	38	4	2.5	90
TTR015	10.06	11.58	1.52	V750444	0.03		0.25	9	3	23	2	2.5	95
TTR015	11.58	13.11	1.52	V750445	0.08		0.25	14	2	171	3	2.5	96
TTR015	13.11	14.63	1.52	V750446	0.02		0.25	6	1	616	1	2.5	58
TTR015	14.63	16.15	1.52	V750447	0.01		0.25	6	1	110	1	2.5	60
TTR015	16.15	17.37	1.22	V750448	0.01		0.25	2.5	4	97	1	2.5	70
TTR015	17.37	18.90	1.52	V750449	0.06		0.25	7	2	97	1	6	93
TTR015	18.90	20.42	1.52	V750451	0.07		0.25	16	3	55	2	5	107
TTR015	20.42	21.95	1.52	V750452	0.08		0.25	16	3	34	8	2.5	61
TTR015	21.95	23.47	1.52	V750453	0.07		0.25	9	6	780	1	2.5	45
TTR015	23.47	24.99	1.52	V750454	0.06		0.25	17	4	762	2	5	44
TTR015	24.99	26.52	1.52	V750455	0.03		0.25	9	1	261	2	5	48
TTR015	26.52	28.04	1.52	V750456	0.01		0.25	8	2	62	1	2.5	41
TTR015	28.04	29.57	1.52	V750457	0.01		0.25	6	4	13	2	2.5	33
TTR015	29.57	31.09	1.52	V750458	0.01		0.25	2.5	4	13	1	2.5	35
TTR015	31.09	32.61	1.52	V750459	0.04		0.25	7	4	82	1	2.5	57
TTR015	32.61	34.14	1.52	V750460	0.13		0.25	19	2	59	5	6	86
TTR015	34.14	35.66	1.52	V750461	0.08		0.25	26	2	97	4	2.5	97
TTR015	35.66	37.19	1.52	V750462	0.06		0.25	20	6	25	3	2.5	105
TTR015	37.19	38.71	1.52	V750463	0.02		0.25	14	2	19	4	5	56
TTR015	38.71	40.23	1.52	V750464	0.005		0.25	8	3	4	4	2.5	40
TTR015	40.23	41.76	1.52	V750466	0.005		0.25	9	3	9	2	9	41
TTR015	41.76	43.28	1.52	V750467	0.01		0.25	10	1	7	1	2.5	58
TTR015	43.28	44.81	1.52	V750468	0.01		0.25	19	3	10	3	2.5	33
TTR015	44.81	46.33	1.52	V750469	0.005		0.25	12	6	22	2	9	27

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR015	46.33	47.85	1.52	V750470	0.005		0.25	10	2	4	1	7	29
TTR015	47.85	49.38	1.52	V750471	0.005		0.25	10	7	6	1	2.5	22
TTR015	49.38	50.90	1.52	V750472	0.005		0.25	12	4	23	7	2.5	43
TTR015	50.90	52.43	1.52	V750473	0.005		0.25	6	4	5	2	2.5	23
TTR015	52.43	53.95	1.52	V750474	0.005		0.25	8	4	3	4	13	23
TTR015	53.95	55.47	1.52	V750475	0.01		0.25	18	5	5	5	9	50
TTR015	55.47	57.00	1.52	V750476	0.79		1.9	132	6	1475	49	10	48
TTR015	57.00	58.52	1.52	V750477	0.76		1.3	146	6	498	63	9	50
TTR015	58.52	60.05	1.52	V750478	0.2		0.25	99	2	58	22	2.5	44
TTR015	60.05	61.57	1.52	V750479	1.06		0.6	182	4	92	72	5	106
TTR015	61.57	63.09	1.52	V750481	2.26	2.46	2.4	637	7	237	160	9	122
TTR015	63.09	64.62	1.52	V750482	2.42	2.87	1.6	567	2	180	320	9	506
TTR015	64.62	66.14	1.52	V750483	1.71		0.9	404	5	105	99	2.5	173
TTR015	66.14	67.67	1.52	V750484	0.92		0.5	152	6	66	40	2.5	103
TTR015	67.67	69.19	1.52	V750485	0.77		0.5	169	5	65	59	2.5	133
TTR015	69.19	70.71	1.52	V750486	2.72	3.33	1.4	667	4	193	393	6	376
TTR015	70.71	72.24	1.52	V750487	0.43		0.25	154	5	54	50	2.5	105
TTR015	72.24	73.76	1.52	V750488	0.12		0.25	44	3	16	12	5	113
TTR015	73.76	75.29	1.52	V750489	1.54		0.25	68	6	21	14	2.5	99
TTR015	75.29	76.81	1.52	V750490	1.06		0.25	95	4	55	18	2.5	104
TTR015	76.81	78.33	1.52	V750491	0.56		0.25	53	3	132	13	2.5	92
TTR015	78.33	79.86	1.52	V750492	0.26		0.25	55	1	26	9	2.5	78
TTR015	79.86	81.38	1.52	V750493	0.23		0.25	80	5	16	15	2.5	73
TTR015	81.38	82.91	1.52	V750494	0.14		0.25	74	1	234	7	7	89
TTR015	82.91	84.43	1.52	V750496	0.19		0.25	41	3	280	5	2.5	66
TTR015	84.43	85.95	1.52	V750497	0.19		0.25	26	2	48	8	6	58
TTR015	85.95	87.48	1.52	V750498	0.79		0.25	36	8	71	10	2.5	65
TTR015	87.48	89.00	1.52	V750499	0.22		0.25	17	1	23	7	2.5	78
TTR015	89.00	90.53	1.52	V750500	1.14		0.25	108	5	47	41	2.5	92
TTR016	0.00	0.91	0.91	V750503	0.01		0.25	8	2	48	9	2.5	87
TTR016	0.91	2.44	1.52	V750504	0.01		0.25	2.5	1	63	7	2.5	92
TTR016	2.44	3.96	1.52	V750505	0.01		0.25	5	2	39	4	2.5	81
TTR016	3.96	5.49	1.52	V750506	0.01		0.25	8	2	51	6	2.5	86
TTR016	5.49	7.01	1.52	V750507	0.01		0.25	6	1	84	5	2.5	91
TTR016	7.01	8.53	1.52	V750508	0.01		0.25	2.5	1	50	4	2.5	92
TTR016	8.53	10.06	1.52	V750509	0.005		0.25	2.5	1	30	4	2.5	73
TTR016	10.06	11.28	1.22	V750511	0.01		0.25	2.5	1	34	1	2.5	82
TTR016	11.28	12.80	1.52	V750512	0.06		0.25	2.5	2	24	5	2.5	76
TTR016	12.80	14.33	1.52	V750513	0.84	0.86	1	127	2	115	632	5	1275
TTR016	14.33	15.85	1.52	V750514	0.92	1.04	1.1	129	1	159	1175	5	1735
TTR016	15.85	17.37	1.52	V750515	0.2		0.25	32	2	14	15	2.5	163
TTR016	17.37	18.90	1.52	V750516	0.07		0.25	20	1	10	11	2.5	149
TTR016	18.90	20.42	1.52	V750517	0.02		0.25	17	1	32	4	6	57
TTR016	20.42	21.95	1.52	V750518	0.01		0.25	9	1	470	2	2.5	49
TTR016	21.95	23.47	1.52	V750519	0.04		0.25	2.5	1	10	4	6	30
TTR016	23.47	24.99	1.52	V750520	0.01		0.25	8	4	11	5	5	20
TTR016	24.99	26.52	1.52	V750521	0.02		0.25	6	2	156	4	5	41
TTR016	26.52	28.04	1.52	V750522	0.03		0.25	11	3	15	1	7	51
TTR016	28.04	29.57	1.52	V750523	0.01		0.25	5	2	11	1	9	80
TTR016	29.57	31.09	1.52	V750524	3.12		1.7	380	5	172	111	11	215
TTR016	31.09	32.61	1.52	V750526	1.12		0.7	181	1	91	66	6	167
TTR016	32.61	34.14	1.52	V750527	5.99	6.12	2.9	491	2	199	391	11	386
TTR016	34.14	35.66	1.52	V750528	8.51	8.87	3.2	551	9	325	344	10	418
TTR016	35.66	37.19	1.52	V750529	1.89		1.3	133	3	124	64	12	152
TTR016	37.19	38.71	1.52	V750530	0.1		0.25	43	2	19	10	6	44
TTR016	38.71	40.23	1.52	V750531	3.02	2.94	2.1	813	5	295	208	18	154
TTR016	40.23	41.76	1.52	V750532	7.86	6.08	4.2	665	14	388	254	12	566
TTR016	41.76	43.28	1.52	V750533	1.55	1.91	1.7	531	3	459	43	11	114
TTR016	43.28	44.81	1.52	V750534	0.56		5.1	282	5	5540	22	16	150
TTR016	44.81	46.33	1.52	V750535	0.4		0.5	32	1	2250	3	5	25
TTR016	46.33	47.85	1.52	V750536	0.05		0.25	7	1	135	2	2.5	59

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR016	47.85	49.38	1.52	V750537	0.04		0.25	7	1	14	1	2.5	35
TTR016	49.38	50.90	1.52	V750538	0.02		0.25	8	1	7	1	5	26
TTR016	50.90	52.43	1.52	V750539	0.005		0.25	5	1	3	1	2.5	19
TTR016	52.43	53.95	1.52	V750541	0.02		0.25	6	1	15	2	6	24
TTR016	53.95	55.47	1.52	V750542	0.005		0.25	2.5	1	3	1	2.5	15
TTR016	55.47	57.00	1.52	V750543	0.01		0.25	2.5	1	3	1	2.5	21
TTR016	57.00	58.52	1.52	V750544	0.01		0.25	2.5	1	2	1	5	16
TTR016	58.52	60.05	1.52	V750545	0.005		0.25	2.5	1	3	1	2.5	15
TTR016	60.05	61.57	1.52	V750546	0.36		0.25	20	1	9	5	2.5	35
TTR016	61.57	63.09	1.52	V750547	0.68		0.25	22	2	5	2	2.5	40
TTR016	63.09	64.62	1.52	V750548	0.21		0.25	30	2	7	2	2.5	23
TTR016	64.62	66.14	1.52	V750549	0.39		0.25	23	4	6	4	2.5	47
TTR016	66.14	67.67	1.52	V750550	0.37		0.25	21	1	9	6	2.5	55
TTR016	67.67	69.19	1.52	V750551	0.09		0.25	17	3	6	4	2.5	57
TTR016	69.19	70.71	1.52	V750552	1.17		0.25	29	1	57	6	2.5	63
TTR016	70.71	72.24	1.52	V750553	0.42		0.25	28	1	22	6	7	69
TTR016	72.24	73.76	1.52	V750554	0.07		0.25	10	1	0.5	2	2.5	49
TTR016	73.76	75.29	1.52	V750556	0.3		0.25	16	1	6	3	2.5	53
TTR017	0.00	2.44	2.44	V750559	0.19		1.4	18	1	80	38	5	706
TTR017	2.44	3.96	1.52	V750560	0.45		0.9	33	1	79	34	8	525
TTR017	3.96	5.49	1.52	V750561	1.1		2.5	46	1	128	51	12	545
TTR017	5.49	7.01	1.52	V750562	0.12		0.7	9	1	67	20	2.5	417
TTR017	7.01	8.53	1.52	V750563	0.06		0.25	19	1	111	16	5	424
TTR017	8.53	10.06	1.52	V750564	0.03		0.25	9	1	65	14	2.5	476
TTR017	10.06	11.58	1.52	V750565	0.04		0.25	14	1	38	25	9	342
TTR017	11.58	13.11	1.52	V750566	0.98		3.2	55	1	128	60	11	479
TTR017	13.11	14.63	1.52	V750567	0.75		1.2	66	2	145	58	11	386
TTR017	14.63	16.15	1.52	V750568	0.03		0.25	11	1	77	9	8	311
TTR017	16.15	17.37	1.22	V750569	0.06		0.25	12	2	30	7	8	204
TTR017	17.37	18.90	1.52	V750571	0.03		0.25	10	1	6	9	2.5	102
TTR017	18.90	20.42	1.52	V750572	0.04		0.25	11	1	560	8	2.5	118
TTR017	20.42	21.95	1.52	V750573	0.04		0.25	7	2	26	7	2.5	82
TTR017	21.95	23.47	1.52	V750574	0.03		0.25	17	1	793	4	2.5	49
TTR017	23.47	24.99	1.52	V750575	0.15		2.2	16	1	4720	6	6	94
TTR017	24.99	26.52	1.52	V750576	0.02		0.25	2.5	1	392	3	2.5	118
TTR017	26.52	28.04	1.52	V750577	0.01		0.25	2.5	1	6	2	2.5	155
TTR017	28.04	29.57	1.52	V750578	0.04		0.25	7	1	27	4	2.5	175
TTR017	29.57	31.09	1.52	V750579	0.15		0.25	27	2	26	6	2.5	177
TTR017	31.09	32.61	1.52	V750580	0.1		0.25	38	2	19	8	2.5	187
TTR017	32.61	34.14	1.52	V750581	0.02		0.25	10	1	22	2	2.5	69
TTR017	34.14	35.66	1.52	V750582	0.15		0.25	63	4	64	4	2.5	76
TTR017	35.66	37.19	1.52	V750583	0.04		0.25	24	1	93	2	2.5	54
TTR017	37.19	38.71	1.52	V750584	0.01		0.25	2.5	1	2	1	5	230
TTR017	38.71	40.23	1.52	V750586	0.01		0.25	6	1	9	6	5	264
TTR017	40.23	41.76	1.52	V750587	0.01		0.25	6	1	21	8	8	273
TTR017	41.76	43.28	1.52	V750588	1.41		1.1	176	6	138	15	2.5	229
TTR017	43.28	44.81	1.52	V750589	1.54		0.25	41	2	37	7	2.5	259
TTR017	44.81	46.33	1.52	V750590	1.91		1.7	251	8	146	14	2.5	1890
TTR017	46.33	47.85	1.52	V750591	7.12	8.62	22.2	460	48	1410	64	14	21200
TTR017	47.85	49.38	1.52	V750592	21.1	23.8	36.7	533	53	1005	120	19	25300
TTR017	49.38	50.90	1.52	V750593	0.48		0.7	175	5	52	16	5	170
TTR017	50.90	52.43	1.52	V750594	0.09		0.25	33	1	11	9	7	102
TTR017	52.43	53.95	1.52	V750595	0.49		0.25	119	3	8	15	8	46
TTR018	0.00	2.44	2.44	V750598	0.13		0.9	21	3	76	26	7	541
TTR018	2.44	3.96	1.52	V750599	0.36		1.4	24	4	98	35	8	684
TTR018	3.96	5.49	1.52	V750601	0.72		1.5	30	2	118	32	2.5	584
TTR018	5.49	7.01	1.52	V750602	0.77		1.5	35	2	139	39	10	476
TTR018	7.01	8.53	1.52	V750603	0.02		0.25	10	3	57	6	2.5	223
TTR018	8.53	10.06	1.52	V750604	0.05		0.25	8	3	57	4	2.5	230
TTR018	10.06	11.58	1.52	V750605	0.01		0.25	2.5	5	56	5	2.5	125
TTR018	11.58	13.11	1.52	V750606	0.01		0.25	5	2	73	7	2.5	233

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR018	13.11	14.63	1.52	V750607	0.005		0.25	5	4	71	6	2.5	197
TTR018	14.63	16.15	1.52	V750608	0.1		0.25	18	1	112	18	2.5	232
TTR018	16.15	17.68	1.52	V750609	1.27		1.9	57	2	110	56	8	326
TTR018	17.68	18.90	1.22	V750610	0.49		1	41	1	95	27	2.5	232
TTR018	18.90	20.42	1.52	V750611	0.3		0.5	27	2	130	13	7	244
TTR018	20.42	21.95	1.52	V750612	2.24		19	211	5	1550	42	106	392
TTR018	21.95	23.47	1.52	V750613	1.34	1.26	3.8	407	2	334	32	33	124
TTR018	23.47	24.99	1.52	V750614	0.29		0.25	48	4	200	10	15	311
TTR018	24.99	26.52	1.52	V750616	0.02		0.25	14	1	30	5	8	96
TTR018	26.52	28.04	1.52	V750617	1.13		0.25	72	3	120	8	8	111
TTR018	28.04	29.57	1.52	V750618	0.08		0.25	36	1	147	6	9	130
TTR018	29.57	31.09	1.52	V750619	0.18		0.25	29	7	19	9	10	150
TTR018	31.09	32.61	1.52	V750620	0.11		0.8	37	2	124	14	7	205
TTR018	32.61	34.14	1.52	V750621	0.03		1.1	21	1	138	11	7	117
TTR018	34.14	35.66	1.52	V750622	0.02		0.9	16	3	33	8	8	121
TTR018	35.66	37.19	1.52	V750623	0.05		0.25	22	1	68	6	7	107
TTR018	37.19	38.71	1.52	V750624	0.01		0.25	11	3	79	5	6	70
TTR018	38.71	40.23	1.52	V750625	0.01		0.25	5	4	58	6	2.5	83
TTR018	40.23	41.76	1.52	V750626	0.005		0.25	6	1	40	4	2.5	74
TTR018	41.76	43.28	1.52	V750627	0.01		0.25	8	3	38	3	2.5	79
TTR018	43.28	44.81	1.52	V750628	0.01		0.25	6	2	28	5	2.5	75
TTR018	44.81	46.33	1.52	V750632	0.01		0.25	6	2	50	3	2.5	75
TTR018	46.33	47.85	1.52	V750633	0.005		0.25	7	4	26	3	2.5	69
TTR018	47.85	49.38	1.52	V750634	0.04		0.25	2.5	1	19	8	2.5	57
TTR018	49.38	50.90	1.52	V750635	0.01		0.25	6	3	11	4	2.5	42
TTR018	50.90	52.43	1.52	V750636	0.01		0.25	2.5	1	16	2	2.5	47
TTR018	52.43	53.95	1.52	V750637	0.01		0.25	2.5	2	14	1	2.5	61
TTR018	53.95	55.47	1.52	V750638	0.005		0.25	6	1	15	4	2.5	48
TTR019	0.00	0.91	0.91	V750639	0.14		0.25	22	5	41	10	2.5	127
TTR019	0.91	2.44	1.52	V750640	0.27		1	33	1	57	25	2.5	288
TTR019	2.44	3.96	1.52	V750641	4.14		8.2	132	10	131	70	8	339
TTR019	3.96	5.49	1.52	V750642	0.58		1	29	2	77	30	2.5	304
TTR019	5.49	7.01	1.52	V750643	0.3		0.6	18	1	109	57	2.5	533
TTR019	7.01	8.53	1.52	V750644	0.07		0.25	11	2	80	13	2.5	756
TTR019	8.53	10.06	1.52	V750646	0.01		0.25	6	3	42	2	2.5	297
TTR019	10.06	11.58	1.52	V750647	0.02		0.25	5	1	136	12	2.5	477
TTR019	11.58	13.11	1.52	V750648	0.26		0.25	14	1	147	26	2.5	495
TTR019	13.11	14.63	1.52	V750649	0.36	0.32	1.4	38	2	346	46	2.5	1090
TTR019	14.63	16.15	1.52	V750650	0.09		0.25	27	1	185	9	2.5	970
TTR019	16.15	17.68	1.52	V750651	0.14		0.25	19	1	93	12	2.5	427
TTR019	17.68	18.90	1.22	V750652	0.12		0.5	47	1	53	11	5	288
TTR019	18.90	20.42	1.52	V750653	0.39		0.7	69	4	89	20	11	936
TTR019	20.42	21.95	1.52	V750654	0.28		0.5	75	2	57	9	5	185
TTR019	21.95	23.47	1.52	V750655	0.06		0.25	26	1	39	7	2.5	178
TTR019	23.47	24.99	1.52	V750656	0.01		0.25	10	4	28	5	2.5	96
TTR019	24.99	26.52	1.52	V750657	0.18		0.25	23	1	37	5	5	81
TTR019	26.52	28.04	1.52	V750658	1.05	1.3	3.3	244	3	417	24	2.5	2010
TTR019	28.04	29.57	1.52	V750659	4.22		1.6	232	5	144	22	2.5	953
TTR019	29.57	31.09	1.52	V750661	0.14		0.25	9	2	4	5	2.5	151
TTR019	31.09	32.61	1.52	V750662	0.01		0.25	9	1	1	4	2.5	356
TTR019	32.61	34.14	1.52	V750663	0.7		0.5	76	4	147	5	2.5	177
TTR019	34.14	35.66	1.52	V750664	1.66	1.46	1.8	164	8	184	14	10	2790
TTR019	35.66	37.19	1.52	V750665	1.44	1.48	1.5	224	2	258	16	5	6690
TTR019	37.19	38.71	1.52	V750666	7.29	6.88	3.2	343	9	508	17	2.5	10700
TTR019	38.71	40.23	1.52	V750667	1.44		2.1	343	4	196	31	9	422
TTR019	40.23	41.76	1.52	V750668	0.96		1.3	276	4	109	25	2.5	128
TTR019	41.76	43.28	1.52	V750669	0.54		2.2	232	1	79	43	7	107
TTR019	43.28	44.81	1.52	V750670	1.73	1.62	3	285	4	157	21	5	2650
TTR019	44.81	46.33	1.52	V750671	0.13		0.7	57	1	39	8	5	153
TTR019	46.33	47.85	1.52	V750672	1.77	1.62	4	415	3	305	34	11	5190
TTR019	47.85	49.38	1.52	V750673	5.1	3.69	8.3	565	9	182	64	16	2980

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR019	49.38	50.90	1.52	V750674	37.2		18.5	471	12	399	73	11	14350
TTR019	50.90	52.43	1.52	V750676	0.83	0.73	2.9	292	1	47	41	9	1290
TTR019	52.43	53.95	1.52	V750677	50.5	49	231	1470	134	4890	11400	1900	71100
TTR019	53.95	55.47	1.52	V750678	9.06	8.06	52.3	1035	8	760	3530	288	11950
TTR019	55.47	57.00	1.52	V750679	0.36		2.3	208	1	37	60	12	194
TTR019	57.00	58.52	1.52	V750680	0.19		0.6	77	1	14	23	28	93
TTR019	58.52	60.05	1.52	V750681	0.15		0.7	61	1	21	20	8	188
TTR019	60.05	61.57	1.52	V750682	1.03		3.5	314	5	355	82	24	177
TTR019	61.57	63.09	1.52	V750683	0.34		2.5	483	1	93	72	12	185
TTR019	63.09	64.62	1.52	V750684	7.56	6.71	100	426	8	1305	544	648	2070
TTR019	64.62	66.14	1.52	V750685	0.07		0.7	14	1	25	10	14	125
TTR019	66.14	67.67	1.52	V750686	0.64		1.2	162	1	174	22	7	201
TTR019	67.67	69.19	1.52	V750687	0.11		0.5	29	1	70	8	2.5	101
TTR020	0.00	2.44	2.44	V750691	0.3		1	49	1	134	31	2.5	304
TTR020	2.44	3.96	1.52	V750692	0.31		0.8	29	1	72	28	2.5	463
TTR020	3.96	5.49	1.52	V750693	0.39		0.8	38	1	126	32	2.5	889
TTR020	5.49	7.01	1.52	V750694	0.2		0.25	12	1	80	9	2.5	360
TTR020	7.01	8.53	1.52	V750695	0.03		0.25	11	1	53	5	2.5	505
TTR020	8.53	10.06	1.52	V750696	0.08		0.25	15	1	87	12	2.5	281
TTR020	10.06	11.58	1.52	V750697	0.09		0.5	14	1	196	13	2.5	716
TTR020	11.58	13.11	1.52	V750698	1.23		2.3	55	1	198	128	2.5	905
TTR020	13.11	14.33	1.22	V750699	0.75		0.6	39	1	96	36	2.5	849
TTR020	14.33	15.85	1.52	V750700	5.57	6.96	6.2	415	12	837	160	5	2120
TTR020	15.85	17.37	1.52	V750701	9.34	13.8	6	852	13	599	348	2.5	636
TTR020	17.37	18.90	1.52	V750702	8.26	8.48	5.6	360	10	1140	94	9	15300
TTR020	18.90	20.42	1.52	V750703	10.65		6.5	243	12	555	36	2.5	1665
TTR020	20.42	21.95	1.52	V750704	28.5	28.2	8.6	357	22	1370	37	6	1080
TTR020	21.95	23.47	1.52	V750706	1.86		0.9	183	5	103	11	2.5	205
TTR020	23.47	24.99	1.52	V750707	0.33		0.5	36	2	395	4	2.5	133
TTR020	24.99	26.52	1.52	V750708	2.8		1.7	178	6	219	23	2.5	153
TTR020	26.52	28.04	1.52	V750709	2.87	2.63	1.9	235	8	445	17	2.5	1890
TTR020	28.04	29.57	1.52	V750710	0.29		0.25	35	1	35	3	6	457
TTR020	29.57	31.09	1.52	V750711	0.02		0.25	14	1	18	3	6	70
TTR020	31.09	32.61	1.52	V750712	0.01		0.25	16	1	31	6	7	105
TTR020	32.61	34.14	1.52	V750713	7.41	1.98	8	502	6	389	707	16	3420
TTR020	34.14	35.66	1.52	V750714	6.69	6.51	2.6	385	4	142	163	6	384
TTR020	35.66	37.19	1.52	V750715	7.76	6.96	3.9	180	7	313	60	7	522
TTR020	37.19	38.71	1.52	V750716	0.07		0.25	14	1	11	24	5	326
TTR020	38.71	40.23	1.52	V750717	0.51		0.7	116	1	70	18	2.5	159
TTR020	40.23	41.76	1.52	V750718	0.21		0.25	68	1	30	10	5	58
TTR020	41.76	43.28	1.52	V750719	0.01		0.25	20	1	6	2	2.5	54
TTR020	43.28	44.81	1.52	V750721	0.03		0.25	20	3	6	6	2.5	42
TTR020	44.81	46.33	1.52	V750722	0.01		0.25	20	1	6	5	7	56
TTR020	46.33	47.85	1.52	V750723	0.11		0.25	49	1	18	16	2.5	63
TTR020	47.85	49.38	1.52	V750724	0.11		0.25	70	1	3	11	2.5	75
TTR020	49.38	50.90	1.52	V750725	1.3		1.7	249	1	55	33	6	131
TTR020	50.90	52.43	1.52	V750726	3.29	3.38	3.9	418	2	189	397	8	1640
TTR020	52.43	53.95	1.52	V750727	6.67		8.7	1090	5	475	366	27	269
TTR020	53.95	55.47	1.52	V750728	0.27		1.6	288	1	81	45	12	74
TTR020	55.47	57.00	1.52	V750729	0.09		0.5	50	1	22	12	9	86
TTR020	57.00	58.52	1.52	V750730	0.61		3.1	176	1	497	156	27	381
TTR020	58.52	60.05	1.52	V750731	7.46	7.1	30.1	798	10	988	1930	191	8410
TTR020	60.05	61.57	1.52	V750732	3.11	3.06	15.7	514	1	234	208	56	1175
TTR020	61.57	63.09	1.52	V750736	0.94	1.03	6.3	429	1	71	142	10	671
TTR020	63.09	64.62	1.52	V750737	0.01		0.25	12	1	5	91	14	383
TTR020	64.62	66.45	1.83	V750738	0.02		0.25	14	1	8	16	6	176
TTR020	66.45	67.67	1.22	V750739	0.04		0.25	11	1	46	47	11	221
TTR020	67.67	69.19	1.52	V750740	0.24		0.25	42	1	43	42	8	200
TTR020	69.19	70.71	1.52	V750741	0.01		0.25	10	1	5	6	8	91
TTR020	70.71	72.24	1.52	V750742	0.01		0.25	6	1	10	2	2.5	58
TTR020	72.24	73.76	1.52	V750743	0.005		0.25	17	1	20	15	2.5	140

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR020	73.76	75.29	1.52	V750744	0.11		0.25	51	1	12	8	2.5	74
TTR020	75.29	76.81	1.52	V750745	0.03		0.25	9	1	22	3	2.5	63
TTR020	76.81	78.33	1.52	V750746	0.01		0.25	8	1	13	3	2.5	84
TTR020	78.33	79.86	1.52	V750747	0.01		0.25	7	1	17	1	2.5	128
TTR021	0.00	2.44	2.44	V750748	1.12		1.1	157	1	123	36	2.5	177
TTR021	2.44	3.96	1.52	V750749	1	0.84	1.4	452	1	127	90	6	377
TTR021	3.96	5.49	1.52	V750751	0.73		0.8	285	1	50	35	2.5	155
TTR021	5.49	7.01	1.52	V750752	1.16	1.06	3.3	432	1	124	94	6	2470
TTR021	7.01	8.53	1.52	V750753	1.31	1.43	3.4	558	3	246	193	7	1650
TTR021	8.53	9.75	1.22	V750754	1.63	1.76	4.8	419	6	391	170	11	5500
TTR021	9.75	11.28	1.52	V750755	0.11		0.25	24	1	66	8	2.5	424
TTR021	11.28	12.80	1.52	V750756	0.02		0.25	19	1	41	4	8	157
TTR021	12.80	14.33	1.52	V750757	0.005		0.25	10	1	12	2	7	113
TTR021	14.33	15.85	1.52	V750758	0.005		0.25	34	1	32	1	2.5	257
TTR021	15.85	17.37	1.52	V750759	0.01		0.25	26	1	25	5	7	85
TTR021	17.37	18.90	1.52	V750760	0.02		0.25	25	1	64	11	6	101
TTR021	18.90	20.42	1.52	V750761	0.03		0.6	51	1	63	8	2.5	305
TTR021	20.42	21.95	1.52	V750762	0.03		0.25	34	1	14	4	9	166
TTR021	21.95	23.47	1.52	V750763	0.9		0.9	117	1	149	17	15	270
TTR021	23.47	24.99	1.52	V750764	0.58		0.6	206	2	68	12	5	230
TTR021	24.99	26.52	1.52	V750766	0.32		0.25	156	1	24	11	8	203
TTR021	26.52	28.04	1.52	V750767	0.96		0.9	113	1	80	24	9	814
TTR021	28.04	29.57	1.52	V750768	0.42		0.25	55	1	14	10	9	122
TTR021	29.57	31.09	1.52	V750769	0.01		0.25	12	1	6	1	15	120
TTR021	31.09	32.61	1.52	V750770	0.17		0.25	175	1	31	7	20	96
TTR021	32.61	34.14	1.52	V750771	0.29		0.5	92	1	72	8	10	57
TTR021	34.14	35.66	1.52	V750772	4.19		2.1	58	2	204	23	15	400
TTR021	35.66	37.19	1.52	V750773	0.07		0.25	25	3	59	5	10	112
TTR021	37.19	38.71	1.52	V750774	0.04		0.7	96	2	36	16	11	340
TTR021	38.71	40.23	1.52	V750775	0.26		0.8	167	1	68	22	12	443
TTR021	40.23	41.76	1.52	V750776	0.02		0.5	19	1	42	10	13	133
TTR021	41.76	43.28	1.52	V750777	0.02		0.25	14	1	13	7	13	216
TTR021	43.28	44.81	1.52	V750778	0.12		1.1	83	1	36	25	13	126
TTR021	44.81	46.33	1.52	V750779	16	14.2	114	587	5	1880	898	735	14750
TTR021	46.33	47.85	1.52	V750781	0.11		1.3	31	1	31	23	17	160
TTR021	47.85	49.38	1.52	V750782	0.11		0.25	9	1	19	5	9	49
TTR021	49.38	50.90	1.52	V750783	0.04		0.25	7	1	7	3	8	75
TTR021	50.90	52.43	1.52	V750784	0.03		0.25	11	1	13	2	6	39
TTR021	52.43	53.95	1.52	V750785	0.03		0.25	5	1	8	3	6	43
TTR021	53.95	55.47	1.52	V750786	0.03		0.25	6	1	10	1	7	73
TTR021	55.47	57.00	1.52	V750787	0.01		0.25	5	1	5	1	7	58
TTR022	0.00	2.44	2.44	V750790	0.44		0.5	88	2	84	22	2.5	143
TTR022	2.44	3.96	1.52	V750791	0.92		1.4	479	6	158	69	2.5	272
TTR022	3.96	5.49	1.52	V750792	0.76	0.77	1.3	456	6	98	68	6	293
TTR022	5.49	7.01	1.52	V750793	1.94	1.73	1.8	416	4	64	63	18	203
TTR022	7.01	8.53	1.52	V750794	12.95		4.3	811	1	200	122	19	448
TTR022	8.53	9.75	1.22	V750796	16.8	11.9	22.2	1775	16	1860	465	66	1655
TTR022	9.75	11.28	1.52	V750797	19.85		26.6	2010	17	2080	497	72	1525
TTR022	11.28	12.80	1.52	V750798	38.6	43.5	22.7	1930	32	2450	324	41	705
TTR022	12.80	14.33	1.52	V750799	2.12		2.1	198	1	258	25	18	484
TTR022	14.33	15.85	1.52	V750800	0.08		0.25	17	1	25	1	5	79
TTR022	15.85	17.37	1.52	V750801	0.05		0.25	32	1	22	8	11	144
TTR022	17.37	18.90	1.52	V750802	0.15		0.25	13	1	17	6	7	165
TTR022	18.90	20.42	1.52	V750803	0.01		0.25	9	1	26	1	6	115
TTR022	20.42	21.95	1.52	V750804	0.02		0.25	11	1	64	7	8	250
TTR022	21.95	23.47	1.52	V750805	0.01		0.25	19	1	63	9	11	257
TTR022	23.47	24.99	1.52	V750806	0.01		0.25	56	1	9	10	14	83
TTR022	24.99	26.52	1.52	V750807	0.6		2.5	62	3	76	19	13	164
TTR022	26.52	28.04	1.52	V750808	0.57		1.3	392	3	40	53	7	78
TTR022	28.04	29.57	1.52	V750809	0.11		0.25	83	1	18	7	5	76
TTR022	29.57	31.09	1.52	V750811	0.7		1.1	139	3	516	24	8	103

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR022	31.09	32.61	1.52	V750812	13.8	4.07	4	433	5	404	109	16	313
TTR022	32.61	34.14	1.52	V750813	0.97		1	272	1	75	29	9	122
TTR022	34.14	35.66	1.52	V750814	44.7	46.9	19.3	1280	15	2490	236	28	265
TTR022	35.66	37.19	1.52	V750815	0.52		0.6	65	1	169	11	10	144
TTR022	37.19	38.71	1.52	V750816	0.14		0.25	43	1	142	7	8	134
TTR022	38.71	40.23	1.52	V750817	0.03		0.25	21	1	37	2	6	30
TTR022	40.23	41.76	1.52	V750818	0.22		1.9	130	1	1365	31	19	157
TTR022	41.76	43.28	1.52	V750819	0.01		0.25	23	1	21	9	6	159
TTR022	43.28	44.81	1.52	V750820	0.02		0.25	11	1	13	4	6	69
TTR022	44.81	46.33	1.52	V750821	0.02		0.25	2.5	1	13	2	2.5	49
TTR022	46.33	47.85	1.52	V750822	0.03		0.25	6	1	3	7	2.5	56
TTR022	47.85	49.38	1.52	V750823	0.7		0.25	148	1	29	10	2.5	70
TTR022	49.38	50.90	1.52	V750824	0.03		0.25	5	1	11	1	2.5	73
TTR022	50.90	52.43	1.52	V750826	0.04		0.25	2.5	1	3	1	2.5	66
TTR022	52.43	53.95	1.52	V750827	0.04		0.25	31	1	14	4	2.5	69
TTR022	53.95	55.47	1.52	V750828	0.01		0.25	7	1	1	1	2.5	49
TTR022	55.47	57.00	1.52	V750829	0.01		0.25	8	1	1	3	2.5	54
TTR022	57.00	58.52	1.52	V750830	0.06		0.25	20	1	3	5	2.5	84
TTR022	58.52	60.05	1.52	V750831	0.03		0.25	9	1	4	3	2.5	155
TTR022	60.05	61.57	1.52	V750832	0.03		0.25	5	1	4	1	2.5	87
TTR022	61.57	63.09	1.52	V750833	0.005		0.25	2.5	1	8	1	2.5	111
TTR022	63.09	64.62	1.52	V750834	0.02		0.25	9	1	19	3	2.5	134
TTR022	64.62	66.14	1.52	V750835	0.09		0.25	2.5	1	15	2	2.5	418
TTR022	66.14	67.67	1.52	V750836	0.18		0.25	16	2	18	3	2.5	73
TTR022	67.67	69.19	1.52	V750837	0.02		0.25	5	1	6	1	2.5	64
TTR022	69.19	70.71	1.52	V750838	0.3		0.25	47	1	52	7	5	102
TTR022	70.71	72.24	1.52	V750839	0.3		0.25	12	3	52	3	2.5	92
TTR022	72.24	73.76	1.52	V750841	0.07		0.25	12	1	10	3	6	85
TTR022	73.76	75.29	1.52	V750842	0.05		0.25	13	2	10	3	5	70
TTR022	75.29	76.81	1.52	V750843	0.03		0.25	8	1	0.5	10	2.5	155
TTR022	76.81	78.33	1.52	V750844	0.2		0.25	41	1	18	8	2.5	53
TTR022	78.33	79.86	1.52	V750845	0.29		0.25	187	1	23	4	2.5	42
TTR022	79.86	81.38	1.52	V750846	0.03		0.25	12	1	7	2	5	29
TTR022	81.38	82.91	1.52	V750847	0.09		0.25	8	1	9	3	2.5	41
TTR023	0.00	2.44	2.44	V750848	0.16		0.6	27	1	98	23	6	132
TTR023	2.44	3.96	1.52	V750849	0.18		0.25	15	1	102	12	2.5	113
TTR023	3.96	5.49	1.52	V750850	0.09		0.25	24	1	45	13	2.5	95
TTR023	5.49	7.01	1.52	V750851	0.39		0.25	113	1	39	29	9	97
TTR023	7.01	8.53	1.52	V750852	0.31		0.25	86	2	24	20	2.5	66
TTR023	8.53	9.75	1.22	V750853	0.64		0.25	135	5	44	31	2.5	75
TTR023	9.75	11.28	1.52	V750854	0.55		0.25	78	3	13	22	2.5	56
TTR023	11.28	12.80	1.52	V750856	0.005		0.25	2.5	3	8	1	2.5	36
TTR023	12.80	14.33	1.52	V750857	0.03		0.25	17	2	11	5	2.5	46
TTR023	14.33	15.85	1.52	V750858	0.06		0.25	14	2	5	4	2.5	61
TTR023	15.85	17.37	1.52	V750859	0.16		0.25	30	2	5	4	2.5	46
TTR023	17.37	18.90	1.52	V750860	0.05		0.25	12	4	4	1	2.5	54
TTR023	18.90	20.42	1.52	V750861	0.01		0.25	12	5	4	1	2.5	75
TTR023	20.42	21.95	1.52	V750862	0.01		0.25	8	1	4	1	2.5	77
TTR023	21.95	23.47	1.52	V750863	0.2		0.25	20	2	52	4	2.5	407
TTR023	23.47	24.99	1.52	V750864	0.49		0.25	160	4	102	33	2.5	484
TTR023	24.99	26.52	1.52	V750865	1.28	1.21	8.1	419	3	190	1180	18	2820
TTR023	26.52	28.04	1.52	V750866	5.69	4.97	4.1	598	7	421	161	9	416
TTR023	28.04	29.57	1.52	V750867	0.49		0.6	121	4	78	215	2.5	734
TTR023	29.57	31.09	1.52	V750868	0.27		0.9	71	1	42	132	6	563
TTR023	31.09	32.61	1.52	V750869	1.19		1.8	239	9	167	107	5	195
TTR023	32.61	34.14	1.52	V750871	1.28		2.2	352	4	192	161	10	427
TTR023	34.14	35.66	1.52	V750872	7.09	7.4	13.7	687	15	592	1120	20	15400
TTR023	35.66	37.19	1.52	V750873	8.37	7.93	7.9	202	1	181	660	26	4890
TTR023	37.19	38.71	1.52	V750874	0.14		0.25	26	3	15	21	2.5	254
TTR023	38.71	40.23	1.52	V750875	0.05		0.5	25	6	10	11	7	107
TTR023	40.23	41.76	1.52	V750876	3.51	3.28	7.3	560	9	206	386	27	4580

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR023	41.76	43.28	1.52	V750877	2.56	2.69	6.2	646	3	166	461	31	3470
TTR023	43.28	44.81	1.52	V750878	0.79		1.4	76	1	42	191	35	601
TTR023	44.81	46.33	1.52	V750879	3.65	3.72	14.4	570	1	189	1865	92	2020
TTR023	46.33	47.85	1.52	V750880	0.77		0.9	59	1	55	36	10	234
TTR023	47.85	49.38	1.52	V750881	0.28		0.6	98	1	81	16	9	177
TTR023	49.38	50.90	1.52	V750882	0.05		0.25	22	1	19	9	7	130
TTR023	50.90	52.43	1.52	V750883	0.03		0.25	16	1	18	4	2.5	112
TTR023	52.43	53.95	1.52	V750884	0.04		0.25	2.5	1	6	4	7	68
TTR023	53.95	55.47	1.52	V750886	0.05		0.25	6	3	6	5	2.5	64
TTR023	55.47	57.00	1.52	V750887	0.04		0.25	7	2	8	1	2.5	85
TTR023	57.00	58.52	1.52	V750888	0.06		0.25	13	1	22	16	5	154
TTR023	58.52	60.05	1.52	V750889	0.12		0.25	61	5	31	9	2.5	111
TTR023	60.05	61.57	1.52	V750890	0.8		0.5	69	3	90	13	6	149
TTR023	61.57	63.09	1.52	V750891	0.03		0.25	31	1	6	5	2.5	66
TTR023	63.09	64.62	1.52	V750892	0.28		1.4	162	1	496	16	8	73
TTR023	64.62	66.14	1.52	V750893	0.03		0.25	8	2	35	4	2.5	123
TTR023	66.14	67.67	1.52	V750894	0.005		0.25	7	1	13	3	2.5	106
TTR023	67.67	69.19	1.52	V750895	0.01		0.25	19	3	27	5	2.5	115
TTR023	69.19	70.71	1.52	V750896	0.02		0.25	10	1	19	6	2.5	122
TTR023	70.71	72.24	1.52	V750897	0.05		0.25	8	4	48	4	2.5	152
TTR023	72.24	73.76	1.52	V750898	0.01		0.25	2.5	1	29	5	2.5	101
TTR023	73.76	75.29	1.52	V750899	0.08		0.25	2.5	1	27	1	2.5	85
TTR023	75.29	76.81	1.52	V750901	0.01		0.25	8	2	23	4	2.5	81
TTR023	76.81	78.33	1.52	V750902	0.01		0.25	7	2	27	1	2.5	103
TTR024	0.00	2.44	2.44	V750905	0.11		0.25	21	3	89	14	10	105
TTR024	2.44	3.96	1.52	V750906	0.18		0.25	34	4	46	13	2.5	96
TTR024	3.96	5.49	1.52	V750907	0.28		0.5	86	1	37	19	2.5	78
TTR024	5.49	7.01	1.52	V750908	0.49		0.25	52	2	9	15	6	42
TTR024	7.01	8.53	1.52	V750909	0.12		0.25	36	2	10	7	10	40
TTR024	8.53	9.75	1.22	V750910	0.07		0.25	31	1	37	7	8	37
TTR024	9.75	11.28	1.52	V750911	0.11		0.25	88	4	42	9	5	39
TTR024	11.28	12.80	1.52	V750912	0.96		1	200	5	49	33	10	86
TTR024	12.80	14.33	1.52	V750913	0.03		0.25	8	1	6	2	2.5	22
TTR024	14.33	15.85	1.52	V750914	0.005		0.25	11	1	5	2	7	18
TTR024	15.85	17.37	1.52	V750916	0.005		0.25	7	1	2	1	6	21
TTR024	17.37	18.90	1.52	V750917	0.005		0.25	5	1	2	3	7	39
TTR024	18.90	20.42	1.52	V750918	0.01		0.25	7	1	1	3	9	42
TTR024	20.42	21.95	1.52	V750919	0.02		0.25	13	2	9	5	7	67
TTR024	21.95	23.47	1.52	V750920	0.02		0.25	28	4	6	4	12	37
TTR024	23.47	24.99	1.52	V750921	0.24		0.25	154	5	13	11	10	43
TTR024	24.99	26.52	1.52	V750922	13.7	46.8	4.9	334	10	410	132	13	152
TTR024	26.52	28.04	1.52	V750923	0.08		0.25	42	1	20	10	15	76
TTR024	28.04	29.57	1.52	V750924	0.08		0.25	16	1	3	5	9	79
TTR024	29.57	31.09	1.52	V750925	0.01		0.25	8	1	1	2	10	65
TTR024	31.09	32.61	1.52	V750926	0.17		0.25	30	2	10	8	12	121
TTR024	32.61	34.14	1.52	V750927	0.05		0.25	31	2	15	11	16	150
TTR024	34.14	35.66	1.52	V750928	1.75	1.75	2	215	6	99	84	15	2380
TTR024	35.66	37.19	1.52	V750929	0.25		0.7	69	1	240	22	13	237
TTR024	37.19	38.71	1.52	V750931	0.03		0.5	27	1	191	8	15	91
TTR024	38.71	40.23	1.52	V751034	0.02		0.25	27	1	154	9	6	75
TTR024	40.23	41.76	1.52	V750932	0.02		0.25	11	2	31	4	11	62
TTR024	41.76	43.28	1.52	V750933	0.03		0.25	9	3	9	3	9	66
TTR024	43.28	44.81	1.52	V750934	0.01		0.25	5	2	8	7	11	85
TTR024	44.81	46.33	1.52	V750935	0.01		0.25	7	2	8	3	7	93
TTR024	46.33	47.85	1.52	V750936	0.03		0.25	7	1	16	6	10	87
TTR024	47.85	49.38	1.52	V750937	0.005		0.25	2.5	2	6	1	2.5	69
TTR024	49.38	50.90	1.52	V750938	0.01		0.25	11	2	19	1	5	29
TTR024	50.90	52.43	1.52	V750939	0.04		0.25	5	4	13	7	2.5	101
TTR024	52.43	53.95	1.52	V750940	0.14		0.25	19	3	12	3	2.5	76
TTR024	53.95	55.47	1.52	V750941	0.05		0.25	2.5	1	6	5	2.5	61
TTR024	55.47	57.00	1.52	V750942	0.02		0.25	27	3	6	3	2.5	46

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR024	57.00	58.52	1.52	V750943	0.07		0.25	101	7	5	2	5	52
TTR024	58.52	60.05	1.52	V750944	0.005		0.25	2.5	5	8	1	2.5	68
TTR024	60.05	61.57	1.52	V750946	0.01		0.25	5	2	6	1	2.5	48
TTR024	61.57	63.09	1.52	V750947	0.16		0.25	54	5	29	2	2.5	45
TTR024	63.09	64.62	1.52	V750948	0.55		0.25	33	3	94	7	2.5	46
TTR024	64.62	66.14	1.52	V750949	0.73		0.25	94	2	13	12	2.5	52
TTR024	66.14	67.67	1.52	V750950	0.18		0.25	2.5	2	6	1	2.5	76
TTR024	67.67	69.19	1.52	V750951	0.02		0.25	2.5	1	1	1	2.5	98
TTR024	69.19	70.71	1.52	V750952	0.05		0.25	5	1	17	3	2.5	147
TTR024	70.71	72.24	1.52	V750953	0.02		0.25	2.5	2	7	5	5	127
TTR024	72.24	73.76	1.52	V750954	0.75		0.25	25	2	60	7	2.5	153
TTR024	73.76	75.29	1.52	V750955	0.01		0.25	2.5	5	13	3	2.5	102
TTR024	75.29	76.81	1.52	V750956	0.02		0.25	2.5	6	13	4	2.5	172
TTR024	76.81	78.33	1.52	V750957	0.08		0.25	2.5	1	16	4	2.5	209
TTR024	78.33	79.86	1.52	V750958	0.22		0.25	12	3	43	16	5	387
TTR024	79.86	81.38	1.52	V750959	0.01		0.25	2.5	1	14	13	2.5	136
TTR024	81.38	82.91	1.52	V750961	0.005		0.25	6	4	1	7	7	204
TTR024	82.91	84.43	1.52	V750962	0.09		0.25	16	1	17	6	2.5	196
TTR024	84.43	85.95	1.52	V750963	0.14		0.25	19	1	26	4	2.5	264
TTR024	85.95	87.48	1.52	V750964	0.76		0.25	14	3	71	1	2.5	580
TTR024	87.48	89.00	1.52	V750965	0.07		0.25	18	4	8	8	2.5	131
TTR024	89.00	90.53	1.52	V750966	0.02		0.25	8	1	19	2	2.5	83
TTR025	0.00	2.44	2.44	V750969	0.07		0.25	12	1	74	10	2.5	115
TTR025	2.44	3.96	1.52	V750970	0.07		0.25	13	2	77	12	2.5	104
TTR025	3.96	5.49	1.52	V750971	0.04		0.25	8	1	48	4	2.5	87
TTR025	5.49	6.71	1.22	V750972	0.12		0.25	33	1	62	14	2.5	94
TTR025	6.71	8.23	1.52	V750973	1.63		0.6	78	2	22	31	2.5	72
TTR025	8.23	9.75	1.52	V750974	0.3		0.25	46	2	9	15	5	48
TTR025	9.75	11.28	1.52	V750976	0.21		0.25	49	1	11	13	2.5	49
TTR025	11.28	12.80	1.52	V750977	0.53		0.5	65	3	52	16	2.5	55
TTR025	12.80	14.33	1.52	V750978	0.31		0.25	53	1	33	11	5	38
TTR025	14.33	15.85	1.52	V750979	0.14		0.5	116	1	17	13	6	47
TTR025	15.85	17.37	1.52	V750980	0.26		0.5	124	1	53	15	2.5	64
TTR025	17.37	18.90	1.52	V750981	0.005		0.25	11	1	3	1	5	15
TTR025	18.90	20.42	1.52	V750982	0.005		0.25	5	1	3	1	2.5	17
TTR025	20.42	21.95	1.52	V750983	0.005		0.25	9	1	9	1	7	17
TTR025	21.95	23.47	1.52	V750984	0.09		0.25	29	1	16	5	6	47
TTR025	23.47	24.99	1.52	V750985	0.12		0.25	54	1	21	9	6	61
TTR025	24.99	26.52	1.52	V750986	1.79		1.3	241	2	51	29	9	59
TTR025	26.52	28.04	1.52	V750987	1.63		1.6	266	1	58	34	5	61
TTR025	28.04	29.57	1.52	V750988	36.7	37.9	85	1010	27	2390	1290	41	15500
TTR025	29.57	31.09	1.52	V750989	1.3		1.3	363	1	85	42	2.5	171
TTR025	31.09	32.61	1.52	V750991	1.1		0.7	35	3	61	14	7	127
TTR025	32.61	34.14	1.52	V750992	0.15		0.25	83	1	12	13	9	100
TTR025	34.14	35.66	1.52	V750993	0.22		0.25	41	1	9	12	9	82
TTR025	35.66	37.19	1.52	V750994	0.1		0.6	34	1	18	32	7	130
TTR025	37.19	38.71	1.52	V750995	0.57		0.7	66	1	56	40	8	154
TTR025	38.71	40.23	1.52	V750996	0.76		1	200	2	121	191	11	366
TTR025	40.23	41.76	1.52	V750997	0.36		1	205	2	37	201	8	391
TTR025	41.76	43.28	1.52	V750998	1.15	1.07	1.8	251	1	88	616	10	2140
TTR025	43.28	44.81	1.52	V750999	1.51		1.3	295	2	153	146	2.5	259
TTR025	44.81	46.33	1.52	V751000	0.7		1.3	219	3	110	341	5	709
TTR025	46.33	47.85	1.52	V751001	0.6		0.7	142	2	44	98	2.5	217
TTR025	47.85	49.38	1.52	V751002	0.33		0.25	44	1	16	19	2.5	115
TTR025	49.38	50.90	1.52	V751003	0.43		0.6	108	4	29	42	7	184
TTR025	50.90	52.43	1.52	V751004	1.67	1.38	1.4	203	1	50	61	2.5	1375
TTR025	52.43	53.95	1.52	V751006	0.08		0.25	41	1	24	11	8	125
TTR025	53.95	55.47	1.52	V751007	0.35		0.5	59	1	38	30	9	190
TTR025	55.47	57.00	1.52	V751008	0.83		2.6	193	1	273	863	12	1365
TTR025	57.00	58.52	1.52	V751009	0.21		1.6	176	1	62	48	15	86
TTR025	58.52	60.05	1.52	V751010	0.08		1	41	1	560	8	10	60

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR025	60.05	61.57	1.52	V751011	0.31		0.8	128	1	74	18	21	125
TTR025	61.57	63.09	1.52	V751012	0.01		0.25	2.5	1	4	2	10	79
TTR025	63.09	64.62	1.52	V751013	0.005		0.25	5	1	13	1	2.5	79
TTR025	64.62	66.14	1.52	V751014	0.005		0.25	2.5	1	9	4	7	62
TTR025	66.14	67.67	1.52	V751015	0.005		0.25	13	1	70	3	8	59
TTR025	67.67	69.19	1.52	V751016	0.005		0.25	6	1	5	1	10	45
TTR025	69.19	70.71	1.52	V751017	0.005		0.25	5	1	18	3	5	43
TTR025	70.71	72.24	1.52	V751018	0.13		0.25	33	1	30	9	2.5	74
TTR025	72.24	73.76	1.52	V751019	0.38		1.8	30	2	2960	7	2.5	71
TTR025	73.76	75.29	1.52	V751021	0.02		0.25	14	1	7	3	2.5	64
TTR025	75.29	76.81	1.52	V751022	0.02		0.25	18	2	9	5	2.5	33
TTR025	76.81	78.33	1.52	V751023	0.13		0.25	19	1	90	5	2.5	54
TTR025	78.33	79.86	1.52	V751024	0.03		0.25	2.5	1	7	4	2.5	104
TTR025	79.86	81.38	1.52	V751025	0.09		0.25	23	1	27	6	6	144
TTR025	81.38	82.91	1.52	V751026	0.02		0.25	7	1	7	5	2.5	134
TTR025	82.91	84.43	1.52	V751027	0.07		0.25	36	1	37	10	6	126
TTR025	84.43	85.95	1.52	V751028	0.02		0.25	2.5	1	37	3	6	68
TTR025	85.95	87.48	1.52	V751029	0.01		0.25	2.5	1	216	6	2.5	75
TTR025	87.48	89.00	1.52	V751030	0.02		0.25	10	1	9	8	2.5	96
TTR025	89.00	90.53	1.52	V751031	0.22		0.25	9	1	33	9	5	101
TTR026	0.00	2.44	2.44	V751036	0.43		0.25	15	6	80	12	2.5	67
TTR026	2.44	3.96	1.52	V751037	0.3		0.25	51	3	104	9	2.5	62
TTR026	3.96	5.18	1.22	V751038	0.03		0.25	16	1	33	7	2.5	58
TTR026	5.18	6.71	1.52	V751039	0.25		0.25	18	1	1110	3	2.5	53
TTR026	6.71	8.23	1.52	V751040	0.03		0.25	8	1	73	1	2.5	52
TTR026	8.23	9.75	1.52	V751041	0.02		0.25	14	1	30	3	2.5	39
TTR026	9.75	11.28	1.52	V751042	0.06		0.25	36	3	85	1	2.5	51
TTR026	11.28	12.80	1.52	V751043	0.1		0.25	57	6	34	5	2.5	41
TTR026	12.80	14.33	1.52	V751044	5.25		7.2	365	13	2160	86	15	88
TTR026	14.33	15.85	1.52	V751045	5.42		14.1	587	12	372	139	62	1825
TTR026	15.85	17.37	1.52	V751046	0.21		0.6	163	2	218	12	5	91
TTR026	17.37	18.90	1.52	V751047	0.05		0.25	32	3	377	5	2.5	43
TTR026	18.90	20.42	1.52	V751048	0.02		0.25	5	1	22	1	2.5	54
TTR026	20.42	21.95	1.52	V751049	0.01		0.25	5	2	23	1	2.5	55
TTR026	21.95	23.47	1.52	V751051	0.02		0.25	2.5	2	5	1	2.5	57
TTR026	23.47	24.99	1.52	V751052	0.02		0.25	2.5	2	31	1	2.5	36
TTR026	24.99	26.52	1.52	V751053	0.02		0.25	2.5	3	303	1	2.5	34
TTR026	26.52	28.04	1.52	V751054	0.005		0.25	2.5	3	8	3	2.5	35
TTR026	28.04	29.57	1.52	V751055	0.01		0.25	6	6	11	1	2.5	30
TTR026	29.57	31.09	1.52	V751056	0.02		0.25	26	1	24	2	2.5	24
TTR027	0.00	2.44	2.44	V751059	0.48		0.5	70	5	38	28	2.5	71
TTR027	2.44	3.96	1.52	V751060	0.17		0.25	34	1	8	4	2.5	41
TTR027	3.96	5.18	1.22	V751061	1.17		0.25	18	5	5	4	2.5	38
TTR027	5.18	6.71	1.52	V751062	0.09		0.25	25	5	7	1	2.5	30
TTR027	6.71	8.23	1.52	V751063	0.05		0.25	5	1	5	1	2.5	40
TTR027	8.23	9.75	1.52	V751064	0.005		0.25	8	2	6	1	2.5	46
TTR027	9.75	11.28	1.52	V751066	0.03		0.25	41	1	39	3	2.5	51
TTR027	11.28	12.80	1.52	V751067	0.03		0.25	64	1	20	7	2.5	48
TTR027	12.80	14.33	1.52	V751068	0.03		0.25	17	3	52	4	2.5	63
TTR027	14.33	15.85	1.52	V751069	0.12		0.25	11	2	35	2	2.5	80
TTR027	15.85	17.37	1.52	V751070	0.02		0.25	37	3	44	9	2.5	88
TTR027	17.37	18.90	1.52	V751071	2.67		1.7	239	4	375	35	9	712
TTR027	18.90	20.42	1.52	V751072	0.27		0.25	194	1	46	27	6	125
TTR027	20.42	21.95	1.52	V751073	0.05		0.25	41	1	20	4	2.5	69
TTR027	21.95	23.47	1.52	V751074	0.005		0.25	6	4	15	1	2.5	62
TTR027	23.47	24.99	1.52	V751075	0.005		0.25	2.5	1	35	1	2.5	56
TTR027	24.99	26.52	1.52	V751076	0.005		0.25	11	1	43	10	2.5	161
TTR027	26.52	28.04	1.52	V751077	0.02		0.25	14	4	66	4	2.5	107
TTR027	28.04	29.57	1.52	V751078	0.01		0.25	8	1	59	5	2.5	132
TTR027	29.57	31.09	1.52	V751079	0.02		0.25	2.5	2	43	1	2.5	235
TTR027	31.09	32.61	1.52	V751081	0.01		0.25	7	1	13	1	2.5	108

Hole	From_m	To_m	Length_m	Sample	Au_ppm_ FireAssay	Au_ppm_ Screen	Ag_ppm	As_ppm	Bi_ppm	Cu_ppm	Pb_ppm	Sb_ppm	Zn_ppm
TTR027	32.61	34.14	1.52	V751082	0.005		0.25	7	1	3	1	2.5	102
TTR027	34.14	35.66	1.52	V751083	0.17		1	84	3	97	9	7	394
TTR027	35.66	37.19	1.52	V751084	6.69		3.8	568	7	211	71	6	156
TTR027	37.19	38.71	1.52	V751085	1.05		0.8	379	1	64	41	9	81
TTR027	38.71	40.23	1.52	V751086	1.82		2.4	190	4	168	40	32	133
TTR027	40.23	41.76	1.52	V751089	0.44		0.6	59	2	44	9	26	71
TTR027	41.76	43.28	1.52	V751087	0.46		1	127	4	97	56	11	193
TTR027	43.28	44.81	1.52	V751088	0.99	1.01	1.8	605	1	258	120	13	242
TTR027	44.81	46.33	1.52	V751090	0.69		0.8	246	2	76	31	20	95
TTR027	46.33	47.85	1.52	V751091	0.02		0.25	37	1	5	1	66	35
TTR027	47.85	49.38	1.52	V751092	0.02		0.25	23	3	141	1	16	69
TTR028	0.00	2.44	2.44	V751096	4.69		11.6	85	7	76	359	29	263
TTR028	2.44	3.96	1.52	V751097	1.48		2.5	111	2	136	97	10	609
TTR028	3.96	5.49	1.52	V751098	0.17		0.25	27	5	107	16	6	334
TTR028	5.49	7.01	1.52	V751099	0.03		0.25	8	1	61	6	2.5	405
TTR028	7.01	8.53	1.52	V751100	0.03		0.25	7	2	69	10	2.5	439
TTR028	8.53	10.06	1.52	V751101	0.01		0.25	7	2	32	1	2.5	184
TTR028	10.06	11.58	1.52	V751102	0.03		0.25	2.5	2	22	1	2.5	129
TTR028	11.58	12.80	1.22	V751103	0.42		1.8	33	1	79	25	7	444
TTR028	12.80	14.33	1.52	V751104	0.18		0.25	19	4	313	13	2.5	797
TTR028	14.33	15.85	1.52	V751105	0.31		0.25	20	3	83	1	2.5	281
TTR028	15.85	17.37	1.52	V751106	0.06		0.25	22	3	111	1	5	214
TTR028	17.37	18.90	1.52	V751107	0.03		0.25	2.5	2	7	1	2.5	89
TTR028	18.90	20.42	1.52	V751108	0.02		0.25	6	5	15	1	2.5	57
TTR028	20.42	21.95	1.52	V751109	0.05		0.25	37	5	19	1	9	65
TTR028	21.95	23.47	1.52	V751111	0.005		0.25	23	1	3	1	14	17
TTR028	23.47	24.99	1.52	V751112	0.17		0.25	18	4	61	1	2.5	83
TTR028	24.99	26.52	1.52	V751113	0.05		0.25	20	4	13	3	2.5	52
TTR028	26.52	28.04	1.52	V751114	0.21		0.25	31	4	69	1	2.5	38
TTR028	28.04	29.57	1.52	V751115	0.15		0.25	29	1	6	1	2.5	38
TTR028	29.57	30.48	0.91	V751116	0.11		0.25	42	3	30	1	2.5	52